### **ELM HYB 26**



# **Technical Data Sheet**

## **ELM HYB 26** *Indoor quality*

ELM HYB 26 is low cure thermosetting powder coating based on polyester and epoxy resins. It has good yellowing resistance combined with excellent overall performance.

#### **Characteristics**

- Low cure
- Good yellowing resistance
- Excellent mechanical properties
- Excellent overall performance
- No VOC

#### **Powder specifications**

 $\begin{array}{lll} \text{-} & \text{Particle size} & < 300 \ \mu\text{m} \\ \text{-} & \text{Average particle size} & 30\text{-}60 \ \mu\text{m} \\ \text{-} & \text{Solids} & > 99\% \end{array}$ 

Density 1,3-1,8 gr/cm³
Storage stability min 12 months

Storage Temperature cool and dry at < 25° C</li>

#### **Applications**

- Factory equipment
- Office furniture
- Ceiling panels
- Household appliances
- Radiators
- Lighting systems
- Shelving components
- Machine elements

#### **Product range**



#### **ELM HYB 26**

#### Surface appearance

Smooth gloss, Smooth semigloss, Smooth semimatt, wrinkle and texture effect

Colors

Mainly RAL, Pantone and NCS shades, special shades on request

#### **Product performance**

To obtain the following data, ELM HYB 26 was coated as follows

Degreased steel 0,5 mm Coating thickness 60-80 µm Object temperature 160 °C 10 min

Test	Method	Result
Impact	ASTM D2794	> 20 kgcm
Erichsen cupping	ISO 1520	> 5 mm
Buchholz hardness	ISO 2815	> 90
Mandrel bending		< 5 mm
Cross-cut adhesion	ISO 2409	GT 0

Condensed water and salt spray test results depend on pre-treatment of metal

- > 400 hrs condensed water test DIN 50017; no infiltration, no blisters for zinc fosfate steel
- > 400 hrs nautral salt spray test ISO 9227; no infiltration, no blisters for zinc fosfate steel

#### **Application instructions**

The substrate to be coated must be free of dirts, oil, rust etc.

For aluminium depending on intended purpose, degreasing or chromatising For steel metal depending on intended purpose, degreasing, Fe –phosphating or Zinc phosphating

ELM HYB 26 can be applied by all commercial electrostatic systems both corona and tribo

#### **Curing Schedule**

Object temperature Retention time at object temperature

150 °C 15 min 160 °C 10 min 170 °C 8 min

DISCLAIMER: All the information given in this technical data sheet is the result of our experience. Application, use and processing of the products take place outside our ability to supervise and therefore exclusively applicator's responsibility. The policy of product development, this specification is subject to change without notice.