

Technical Data Sheet

ELM PUR60 *Outdoor quality*

ELM PUR60 is thermosetting powder coating based on saturated polyurethane resin base, the corresponding hardener plus special heat, light and chalk resistant pigments. Thanks to high crosslink density and special resin technology, it has very good outdoor durability and chemical resistance.

Characteristics

- Very good weather resistance
- Very good chemical resistance
- Anti-graffiti property
- Good general resistance properties
- No VOC

Powder specifications

- Particle size < 300 µm
- Average particle size 30-60 µm
- Solids > 99%
- Density 1,3-1,8 gr/cm³
- Storage stability min 24 months
- Storage Temperature cool and dry at < 25° C

Applications

- Facade elements, window profiles
- Automotive parts
- Street and garden furniture
- Public transport stations
- Doors

Product range

Surface appearance

Smooth gloss, Smooth semigloss , Crocodile and Snake pattern

ELM PUR60



Colors

Mainly RAL, Pantone and NCS shades, special shades on request

Product performance

To obtain the following data, ELM PUR60 was coated as follows

Degreased steel 0,5 mm
Coating thickness 60-80 µm
Object temperature 200 °C 15 min

Test	Method	Result
Impact	ASTM D2794	> 20 kgcm
Ericksen cupping	ISO 1520	> 5 mm
Buchholz hardness	ISO 2815	> 90
Mandrel bending		< 5 mm
Cross-cut adhesion	ISO 2409	GT 0

Condensed water and salt spray test results depend on pre-treatment of metal
> 400 hrs condensed water test DIN 50017; no infiltration, no blisters for zinc fosfate steel
> 400 hrs nautral salt spray test ISO 9227; no infiltration, no blisters for zinc fosfate steel
> 1000 hrs nautral salt spray test ISO 9227; no infiltration, no blisters for chromated aluminium

Application instructions

The substrate to be coated must be free of dirt, oil, rust etc.

For aluminium depending on intended purpose, degreasing or chromatising

For steel metal depending on intended purpose, degreasing, Fe –phosphating or Zinc phosphating

ELM PUR60 can be applied by all commercial electrostatic systems both corona and tribo

Curing Schedule

Object temperature	Retention time at object temperature
190 °C	20 min
200 °C	15 min
210 °C	10 min

DISCLAIMER: All the information given in this technical data sheet is the result of our experience. Application, use and processing of the products take place outside our ability to supervise and therefore exclusively applicator's responsibility. The policy of product development, this specification is subject to change without notice.